

CHEMICAL RESISTANCE PROPERTIES RUBBER STAIR TREAD STRINGER - RISER

ASTM F 925 Methodology

Chemical		Chemical Strength	1 Minute	24 hour
Betadine Cleanser	povidone	7.50%	No Change	Slight change
Betadine Solution	povidone	10.00%	Slight Change	Stain
	iodine	1.00%	Slight Change	Stain
Coal Tar (bitumen)			Slight Change	Stain
House hold ammonia solution		5.00%	No Change	No Change
Household bleach solution		5.25%	No Change	Whitening
Hydrochoric acid solution		5.00%	Very Slight Discoloration	Discoloration
Kerosene			Yellow Stain	Yellow Stain
Olive oil (light)			No Change	No Change
Phenol		5.00%	No Change	No Change
Phenox No. 6925 Phenolic germicideal deterger (0-phenyphenol .45% oBenzyl-p-Cholory (Contains: 0.48% - 3.30%) Lalema	phenol 3.3%)	5.00%	No Change	No Change
Polyguat No. 6750 - 1.00% as recomme Germicidal fungicidal virucidal detergent (Didecyl dimethyl ammonium chloride) (Contains: 3.85%) Lalema	ended	1.00%	No Change	No Change
Polyguat No. 6750 - pure solution Germicidal fungicidal virucidal detergent (Didecyl dimethyl ammonium chloride) (Contains: 3.85%) Lalema		100.00%	No Change	No Change
Rubbing alcohol		70.00%	No Change	No Change
Silver nitrate (normal)			Brown Stain	Dark Brown Stain
Sodium Hydroxide solution		5.00%	No Change	No Change
Sulfuric acid solution		5.00%	Very Slight Discoloration	Discoloration
Unleaded Gasoline (regular grade)			Slight Swelling	Swelling
Wright's Blood Stain** applied directly to the floor			Blue Stain	Blue Stain
White mineral oil (medicinal grade)			No Change	No Change
White vinegar		5.00%	No Change	No Change
lodine solution (tincture of iodine)		2.50%	Yellow Stain	Yellow Stain

Note: The results can vary for different colors.

VPI Corporation 3123 So. 9th Street, P.O. Box 0451 Sheboygan, Wisconsin 53082-0451 U.S.A.

VPI Technical Service: (800) 874-4240