



**Basic ASTM F925 Chemical Resistance - Wall Base
Stringer, Risers & Vinyl Treads**

Chemical	<u>Vinyl Wall Base Stringer & Riser</u>		<u>Vinyl Wall Base Stringer & Riser</u>		<u>Vinyl Wall Base Stringer & Riser</u>	
	1 Minute	24 Hour	1 Minute	24 Hour	1 Minute	24 Hour
Household Ammonia (5% NH ₄ OH)	0	0	0	0	0	0
Household Bleach (5% NaOCl)	0	0	0	0	0	0
Unleaded Gasoline	0	0	SD2	SD1	SA1	0
Hydrochloric Acid 5%	0	SD1	0	0	0	0
Rubbing Alcohol (70% Isopropyl)	0	SD1	0	0	0	SD1
Kerosene	0	SA1	SD1	SA1	0	SA1
Mineral Oil	0	0	0	SD1	0	SD2
Olive Oil	0	0	0	SA1	0	SD2
Disinfectant (5% Phenol)	0	SD1	0	SD1	0	0
Sodium Hydroxide 5%	0	0	0	0	0	SA1
Sulfuric Acid 5%	0	SD2	0	0	0	0
Vinegar (White - 5% Acetic Acid)	0	SD1	0	0	0	SD1
<u>Categories:</u>					<u>Ratings</u>	
SD = Surface Dulling - loss of gloss					0 = no change	
CC = Color Change - discoloration, bleaching, staining ...					1 = slight change	
SA = Surface Attack - swelling, softening, blistering ...					2 = moderate change	
					3 = severe change	